

# BEAUTY & QUALITY... NATURALLY BY



## **REBUTTED/REJOINTED Shingles**



These products are manufactured specifically for exterior and interior wall surface uses. They are a low maintenance product that adds beauty, texture, durability and insulating qualities to either new construction or remodelling and renovation of existing structures





Watkins Sawmills Ltd. Appearance: Machine grooved for a shake texture from Number 1 Grade Blue Label CERTIGRADE

red cedar shingles, trimmed for parallel edges with butts sawn at right angles.

**Finishes:** Natural, primed white, primed gray, or special order colors.

**Lengths:** 16-inch, 18-inch and 24-inch.

### **NUMBER 1 GRADE, BLUE LABEL**

**Description:** Lengths 16-inch, 18-inch, 24-inch; width 14" maximum, 4" minimum;

thickness of 16-inch is 5/2" (5 butts together measures 2" thick),

18-inch is 5/2-1/4" thick, 24-inch is 4/2" thick. Clear heartwood: 100% edge grain; no defects.

**Recommended Use:** For exterior or interior walls where a superior quality product is desired.

**Wall Exposure Table:** 

Max. Weather Exposure		
Shingle Length	Single Course	Double Course
16"	7"	12"
18"	8"	14"
24"	101/2"	16"

## **REBUTTED/REJOINTED Shingles**

Appearance: Manufactured from Number 1 Grade Blue label or Number 2 Grade Red label

CERTIGRADE red cedar shingles, trimmed for parallel edges with butts sawn

at right angles. Available in both sawn and sanded face textures.

**Finishes:** Natural, primed white, primed gray, or special order colors.

**Lengths:** 16-inch, 18-inch and 24-inch.

## **NUMBER 1 GRADE, BLUE LABEL**

Description: Lengths 16-inch, 18-inch, 24-inch; width 14" maximum, 4" minimum; thickness

of 16-inch is 5/2" (5 butts together measures 2" thick), 18-inch is 5/2-1/4" thick,

24-inch is 4/2" thick. Clear heartwood: 100% edge grain; no defects.

Recommended Use: For exterior or interior walls where a superior quality product is desired.

#### **NUMBER 2 GRADE, RED LABEL**

**Description:** Lengths 16-inch, 18-inch, 24-inch; thickness of 16-inch is 5/2"

(5 butts together measures 2" thick), 18-inch is 5/2-1/4" thick, 24-inch is 4/2" thick. Width 14" maximum, 4" minimum; Face must be 10", 11" and 16" or better on 16-inch, 18-inch and 24-inch shingles, respectively. Limited sapwood and flat grain are allowed. Limited knots and defects are allowed above the clear portion.

Recommended Use: For exterior or interior walls where a good quality product is desired.

Wall Exposure Table-No. 1 Grade, Blue Label\*:

\*Maximum weather exposure for No. 2 Grade, Red Label Rebutted and Rejointed shingles should be in accordance with the manufacturer's recommendations.

Max. Weather Exposure		
Shingle Length	Single Course	Double Course
16"	7"	12"
18"	8"	14"
24"	101/2"	16"

- These red cedar shakes and shingles are manufactured in accordance with standards established by the Cedar Shake and Shingle Bureau.
- This is only a product description necessary for selection of materials and grades. For a new roof construction manual and/or wall manual please contact:



Telephone: (604) 462-7116 • Fax: (604) 462-7162 Email: Sales@watkinsawmills.com Toll Free: 1-800-663-8301

PO Box 3280, Mission, British Columbia V2V 4J4

Email: Sales@watkinsawmills.com
Toll Free: 1-800-663-8301

Sawmills Ltd.

Watkins Sawmills Ltd.